



Lion Elastomers LLC

1615 Main Street • P.O. Box 667 • Port Neches, TX 77651
800 / 535-9960 • www.lionelastomers.com

SBR 1712L Elastomer

Product Data

SBR 1712L is a general-purpose cold polymerized elastomer extended with 37.5 parts of highly aromatic oil. It is a low Mooney viscosity version of SBR 1712. It has excellent processing properties and superior polymer stability.

Unique Features

- ▶ Cold polymerized styrene-butadiene elastomer
- ▶ Lower viscosity, Oil extended for improved processing

Applications

- ▶ Passenger & heavy-service treads
- ▶ Retread rubbers and bicycle tires
- ▶ Molded & extruded goods, and wire and cable

Typical Properties

<u>Property</u>	<u>Test Method</u>	<u>Typical</u>
Bound Styrene, Weight %	ASTM D5775	22.5 – 24.5
Mooney viscosity, MML 1+4 (100°C)	ASTM D1646	30 - 40
Oil, Weight %	ASTM D5774	25.8 – 28.8
Oil, type.....	Highly Aromatic	
Organic acid, Weight %	ASTM D5774	4.0 – 6.0
Soap, Weight %	ASTM D5774	0.5 Max.
Ash, Weight %	ASTM D5667	0.70 Max.
Volatile matter, Weight %	ASTM D5668	0.75 Max.
Emulsifier	—	Mixed acid
Coagulant	—	Acid
Stabilizer	—	Staining
Specific gravity, g/cc (bale).....	—	0.95
Physical form*, lbs/bale	—	80.0 (36 kg)

SBR 1712L is recommended for such diverse applications as passenger and heavy-service treads, retread rubbers, bicycle tires, molded and extruded goods, automotive products, seals, hard rubber and wire and cable.

* This product is available in 80 lb rectangular bales individually wrapped in 1.5 mil, low melting point film and shipped in cardboard containers.

Note: Antioxidant is added to this polymer to provide protection during manufacture and storage. The end user's process may require additional antioxidant protection.

SBR 1712L Elastomer

Rheometric Properties (MDR 2000 rheometer)

Test Method – ASTM D5289**

<u>Property</u>	<u>Result</u>
M _L lbf-in	0.5 – 2.5
dN-m	0.6 – 2.8
M _H lbf-in	9.7 – 13.7
dN-m	11.0 – 15.5
t _s 1, minutes	4.4 – 6.4
t' 50, minutes	6.6 – 10.6
t' 90, minutes	11.7 – 16.7

<u>Test Formula (ASTM D3185 2B)</u>	<u>Quantity, Parts by Mass</u>	<u>Material</u>
SBR 1712L oil-extended elastomer	137.50	
Zinc oxide	3.00	IRM 91A
Sulfur	1.75	IRM 031
Stearic acid	1.00	IRM 021
Oil furnace black	68.75	IRB #8
TBBS	1.38	IRM 003

**160°C, 1°Arc

SBR 1712L is a lower Mooney viscosity, general-purpose cold polymerized, oil-extended elastomer. It has excellent processing properties and superior polymer stability. SBR 1712L is recommended for applications such as passenger and heavy-service treads, retread rubbers, bicycle tires, molded and extruded goods, automotive products, seals, hard rubber and wire and cable.

Notice: All information supplied by or on behalf of Lion Elastomers LLC in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Elastomers LLC assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Elastomers LLC for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.