



Lion Elastomers LLC

1615 Main Street • P.O. Box 667 • Port Neches, TX 77651  
800 / 535-9960 • www.lionelastomers.com

## SBR 4684 Elastomer

## Product Data

SBR 4684 is a developmental carbon black master batch (CBMB) containing N-234 carbon black. It has a low level of oil extension and provides characteristics including good abrasion resistance, high physical properties and smooth processing. **Product is made to order on demand.**

### Unique Features

- ▶ Cold polymerized styrene-butadiene elastomer
- ▶ Carbon black master batch
- ▶ Low level extender oil

### Applications

- ▶ Premium truck tire treading
- ▶ Mechanical rubber goods

### Typical Properties

<u>Property</u>	<u>Test Method*</u>	<u>Typical</u>
Polymer, parts .....	—	100
Carbon black, N-234 .....	—	52
Oil, parts – Hi aromatic .....	—	10
Mooney viscosity, UMS 4+4 (100°C) .....	—	49 - 77
Bound Styrene, Weight % .....	—	22.5 – 24.5
Organic acid, Weight % .....	—	3.1 – 5.1
Soap, Weight % .....	—	0.50 Max.
Ash, Weight % .....	—	0.50 Max.
Volatile matter, Weight % .....	ZS 1008K	0.50 Max.
Carbon black, Weight % .....	—	30.6 – 33.6
Emulsifier .....	—	Mixed acid
Coagulant .....	—	Acid
Stabilizer .....	—	Staining
Specific gravity, g/cc (bale).....	ASTM D-792	1.11
Physical form**, lbs/bale .....	—	90.0 (41 kg)

**SBR 4684 is a developmental carbon black master batch containing N-234 carbon black. Low level of oil extension enables good abrasion resistance, high physical properties and smooth processing. Top applications include truck tire treads and mechanical rubber goods.**

\* Company Test Methods

\*\* This product is available in 90 lb rectangular bales individually wrapped in 1.5 mil, low melting point film and shipped stretch wrapped on a wooden pallet. Bales are dipped.

**Note:** Antioxidant is added to this polymer to provide protection during manufacture and storage. The end user's process may require additional antioxidant protection.

## SBR 4684 Elastomer

### Rheometric Properties (MDR 2000 rheometer)

<u>Property</u>	<u>Result</u>
M <sub>L</sub> lbf-in .....	0.7 – 2.7
dN-m .....	0.8 – 3.1
M <sub>H</sub> lbf-in .....	14.5 – 18.5
dN-m .....	16.4 – 20.9
t <sub>s</sub> 1, minutes .....	2.9 – 4.9
t' 50, minutes .....	5.5 – 9.5
t' 90, minutes .....	10.2 – 15.2

### MRG Test Recipe (ASTM 3186)

	<u>Weight</u>	<u>Reference</u> <u>Material</u>
SBR 4684 oil-extended, CBMB elastomer .....	162	
Zinc oxide .....	3.0	IRM-91A
Sulphur .....	1.75	IRM-031
Stearic acid .....	1.50	IRM-021
TBBS .....	1.25	IRM-003

**SBR 4684 is a developmental carbon black master batch containing N-234 carbon black and a low level of oil extension. Recommended applications include truck tire treads and mechanical rubber goods.**

**Product is made to order on demand.**

---

**Notice:** All information supplied by or on behalf of Lion Elastomers LLC in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Elastomers LLC assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Elastomers LLC for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.