



Lion Elastomers LLC

1615 Main Street • P.O. Box 667 • Port Neches, TX 77651
800 / 535-9960 • www.lionelastomers.com

SBR 1888 Elastomer

Product Data

SBR 1888 is a carbon black master batch (CBMB) based on SBR 1712 latex and 82.5 parts N-339 carbon black similar to SBR 1848 but extended with low PCA RAE extender oil. It provides tensile properties greater than equivalent CBMB produced with HAF or HAF-H carbon black, and superior abrasion resistance.

Unique Features

- ▶ Cold polymerized styrene-butadiene elastomer
- ▶ Carbon black master batch
- ▶ RAE extender oil

Applications

- ▶ Tire treading
- ▶ Mechanical rubber goods

Typical Properties

<u>Property</u>	<u>Test Method*</u>	<u>Typical</u>
Polymer, parts	—	100
Carbon black, N-339	—	82.5
Oil, parts – RAE	—	62.5
Mooney viscosity, UMS 4+4 (100°C)	—	46 - 66
Bound Styrene, Weight %	—	22.5 – 24.5
Organic acid, Weight %	—	1.8 – 3.8
Soap, Weight %	—	0.5 Max.
Ash, Weight %	—	0.50 Max.
Volatile matter, Weight %	ZS 1008K	0.75 Max.
Carbon black, Weight %	—	32.2 – 35.2
Emulsifier	—	Mixed acid
Coagulant	—	Acid
Stabilizer	—	Staining
Specific gravity, g/cc (bale).....	ASTM D-792	1.14
Physical form**, lbs/bale	—	90.0 (41 kg)

SBR 1888 is a carbon black master batch based with N-339 carbon black and with low PCA RAE extender oil. It is recommended in a variety of rubber goods such as passenger tread compounds, retreads and mechanical rubber goods.

* Company Test Methods

** This product is available in 90 lb rectangular bales individually wrapped in 1.5 mil, low melting point film and shipped stretch wrapped on a wooden pallet. Bales are dipped.

Note: Antioxidant is added to this polymer to provide protection during manufacture and storage. The end user's process may require additional antioxidant protection.

SBR 1888 Elastomer

Rheometric Properties (MDR 2000 rheometer)

<u>Property</u>	<u>Result</u>
M _L lbf-in	
dN-m	
M _H lbf-in	
dN-m	
t _s 1, minutes	
t' 50, minutes	
t' 90, minutes	

Test Formula (ASTM 3186)

<u>Test Formula (ASTM 3186)</u>	<u>Quantity,Parts</u>	<u>Material</u>
	<u>by Mass</u>	
SBR 1888 oil-extended, CBMB elastomer	245	
Zinc oxide	3.0	IRM 91A
Sulfur	1.75	IRM 031
Stearic acid	1.5	IRM 021
TBBS	1.25	IRM 003

SBR 1888 is a carbon black master batch (CBMB) based on SBR 1712 latex and 82.5 parts N-339 carbon black similar to SBR 1848 but extended with low PCA RAE extender oil. It is used in applications such as tire treads, conveyor belts and mechanical rubber goods.

Notice: All information supplied by or on behalf of Lion Elastomers LLC in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Elastomers LLC assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Elastomers LLC for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.