

Lion Copolymer Geismar, LLC

36191 Highway 30 • Geismar , LA 70734 800 / 535-9960 • www.lionelastomers.com

Royalene® 515 EPDM

Product Data

" An Ultra Fast Curing Polymer for Automotive Extrusions"

Unique Features

- High unsaturation Ultra fast cure rate
- Excellent compression set resistance in closed cell sponge extrusions
- Excellent low temperature properties
- ▶ Co-cures well with SBR
- Non-staining
- Friable bale form for rapid mixing in internal mixers and excellent dispersion properties
- ▶ Excellent weathering resistance

Applications

- ▶ Closed cell sponge profile extrusions
- Closed cell sheet sponge
- Automotive window channel extrusions

Raw Polymer Properties and Specifications

	Test Method*	Typical
Mooney Viscosity, ML (1+4)/150°C (Unmilled)	ZS 1220C	82
E/P Weight Ratio	ZS 1231	62/38
ENB, Weight %	ZS 1222	9.5
Molecular Weight Distribution	ZS 1296A	Medium
Volatile Matter, Weight %	ZS 1008K	0.7 Max.
Stabilizer	_	Non-Staining
Specific Gravity, g/cc	ASTM D-792	0.86
Color	ZS 1072A	Off-White
Physical Form, lbs/bale	_	55.1 (25 kg)
		(Friable bale)

^{*} Company Test Methods R-515

HWY 5/18