

Lion Copolymer Geismar, LLC

36191 Highway 30 • Geismar , LA 70734 800 / 535-9960 • www.lionelastomers.com

# Royalene<sup>®</sup> 868XE EPDM

## **Product Data**

"An Excellent Polymer for Hose and Extruded Profiles "

#### **Unique Features**

- Fast Curing
- Excellent extrusion properties: low die swell, high extrusion rate
- ► High green strength, excellent shape stability
- Friable bale provides excellent dispersion
- Highly extendable
- Good low temperature properties

#### Applications

- Extruded Profiles
- Hose
- Molded Products

### **Raw Polymer Properties**

	Test Method*	Typical
Mooney Viscosity, ML (1+4)/150°C (Unmilled)	ZS 1220C	67
Mooney Viscosity, ML (1+4)/125°C (Unmilled)	ZS 1220B	90
E/P Weight Ratio	ZS 1231	72/28
ENB, Weight %	ZS 1222	6.0
Molecular Weight Distribution	ZS 1296A	Medium
Volatile Matter, Weight %	ZS 1008K	1.0 Max.
Stabilizer	—	Non-Staining
Specific Gravity, g/cc	ASTM D-792	0.87
Color	ZS 1072A	Off White
Physical Form, lbs/bale	—	55.1 (25 kg)
		(Friable bale)

\* Company Test Methods

Royalene 868XE-LE

HWY 5/18

Notice: All information supplied by or on behalf of Lion Copolymer Geismar, LLC in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Copolymer Geismar, LLC assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Copolymer Geismar, LLC for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.