

Product Data Sheet

Royalene™ 556 EPDM

Unique Features

- Excellent extrusion properties: low die swell, high extrusion rate
- High green strength, excellent shape stability
- Friable bale provides excellent dispersion
- Highly extendable
- Good low temperature properties

Applications

- Extruded Profiles
- Hose
- Molded Products

Raw Polymer Properties

Property	Typical Value	Units	Test Methods*
Mooney Viscosity, ML (1+4) / 125°C (Milled)	60	MU	ZS 1223B
E/P Weight Ratio	71/29	—	ZS 1231
Ethylene	67.8	wt%	ZS 1231
ENB	4.5	wt%	ZS 1222
Molecular Weight Distribution	Medium	—	ZS 1296A
Volatile Matter	1.0 Max.	wt%	ZS 1008K
Stabilizer	Non-Staining	—	—
Specific Gravity	0.87	g/cm ³	ASTM D-792
Color	Off White	—	ZS 1072A
Physical Form	25 (Friable bale)	kg/bale	—

* Internal Test Methods

Notice: All information supplied by or on behalf of Lion Elastomers in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Elastomers assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Elastomers for any infringement of the rights owned or controlled by a third party in intellectual, industrial, or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.