

Product Data Sheet

Royalene[™] 505 EPDM

Unique Features

- High unsaturation - Ultra fast cure rate
- Medium range plasticity allows for use in both extrusion and molding applications.
- Co-cures well with SBR and NR
- Non-staining
- . Excellent low temperature properties and weathering resistance
- Mixes quickly in internal mixers with excellent dispersion.
- Suitable for food contact applications. See Royalene™ FDA compliance summary for details .

Applications

- Closed cell sponge profile extrusions
- Closed cell sheet sponge
- Automotive closed cell sponge molded weatherstrip assembly corners
- Molded open cell sponge
- Tire components, such as cover strips, white sidewalls and black sidewalls, in blends with diene polymers.

Raw Polymer Properties

Property	Typical Value	Units	Test Methods*
Mooney Viscosity, ML (1+4) / 125°C (Unmilled)	55	MU	ZS 1220B
E/P Weight Ratio	60/40	_	ZS1231
Ethylene	55	wt%	ZS 1231
ENB	8.0	wt%	ZS 1222
Molecular Weight Distribution	Narrow	_	ZS 1296A
Volatile Matter	0.7 Max	wt%	ZS 1008K
Stabilizer	Non-Staining		—
Specific Gravity	0.86	g/cm ³	ASTM D-792
Color	White/off white		ZS 1072A
Physical Form	25 (Dense bale)	kg/bale	<u> </u>
* Internet Test Mathemate			

* Internal Test Methods

Notice: All information supplied by or on behalf of Lion Elastomers in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Elastomers assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Elastomers for any infringement of the rights owned or controlled by a third party in intellectual, industrial, or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.

> 36191 Highway 30 | P.O. Box 397 Geismar, Louisiana 70734-3526 www.lionelastomers.com

Phone: +1 800.535.9960