

Product Data Sheet

Royalene™ 674 EPDM

Unique Features

- Blends readily with polyolefins for TPO and TPV compounds
- Provides enhanced compression set and good color in TPV
- Highly extendable
- Good aging properties
- Good shape retention in extruded applications
- Very high molecular weight base polymer
- High green strength over a broad temperature range
- Useful for making low hardness compounds
- Extended with a white, hydrotreated paraffinic oil

Applications

- TPO and TPV
- Automotive applications
- Mechanical goods
- Hose, tubes, Profile extrusions

Raw Polymer Properties

Property	Typical Value	Units	Test Methods*
Mooney Viscosity, ML (1+4) / 125°C (Unmilled)	53	MU	ZS 1220B
E/P Weight Ratio	63/37	—	ZS 1231
Ethylene	60.2	wt%	ZS 1231
ENB	4.5	wt%	ZS 1222
Molecular Weight Distribution	Medium	—	ZS 1296A
Oil Extension	75	phr	ZS 1297
Volatile Matter	0.8 Max.	wt%	ZS 1008K
Stabilizer	Non-Staining	—	—
Specific Gravity	0.87	g/cm ³	ASTM D-792
Color	Off White	—	ZS 1072A
Physical Form	25 (Dense bale)	kg/bale	—

* Internal Test Methods

Notice: All information supplied by or on behalf of Lion Copolymer Geismar, LLC in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Copolymer Geismar, LLC assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Copolymer Geismar, LLC for any infringement of the rights owned or controlled by a third party in intellectual, industrial, or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.