

Lion Elastomers LLC

1615 Main Street • P.O. Box 667 • Port Neches, TX 77651 800 / 535-9960 • www.lionelastomers.com

## SBR 1012 Elastomer

Hot polymerized SBR 1012 elastomer is particularly useful as a binder for fibrous materials. It imparts increased cohesive strength when added to an adhesive mixture.

## **Unique Features**

- Hot polymerized styrene-butadiene elastomer
- Broad molecular weight makes dissolving easier
- ► High Mooney and higher solution viscosity

## **Applications**

- Binder for fibrous materials
- Pressure sensitive and tape adhesives
- General purpose adhesives

## **Typical Properties**

Property	Test Method*	<u>Typical</u>
Mooney viscosity, MML 1+4 (100°C)	—	105 - 135
Solution viscosity, cP (aged, 4% Toluene solution)	—	500 Max.
Bound Styrene, Weight %	—	22.5 – 24.5
Organic acid, Weight %	—	4.0 - 6.0
Soap, Weight %	—	0.5 Max.
Ash, Weight %	—	1.5 Max.
Volatile matter, Weight %	ZS 1008K	1.0 Max.
Emulsifier	_	Fatty acid
Coagulant	—	Acid
Stabilizer	_	Non-Staining
Specific gravity, g/cc (bale)	ASTM D-792	0.94
Color	_	Off White
Physical form**, lbs/bale	—	70.0 (32 kg)

SBR 1012 elastomer is used as a binder for fibrous materials. It imparts increased cohesive strength when added to an adhesive mixture. Also available in crumb form.

\* Company Test Methods

\*\* This product is available in 70 lb rectangular bales individually wrapped in 1.5 mil, low melting point film and shipped in two cell cardboard containers.

**Note:** Antioxidant is added to this polymer to provide protection during manufacture and storage. The end user's process may require additional antioxidant protection.

Notice: All information supplied by or on behalf of Lion Elastomers LLC in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Elastomers LLC assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or products, whether in the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.