



Lion Elastomers LLC

1615 Main Street • P.O. Box 667 • Port Neches, TX 77651  
800 / 535-9960 • www.lionelastomers.com

## SBR 1778 Elastomer

## Product Data

SBR 1778 is a general-purpose cold polymerized, naphthenic oil-extended elastomer. It exhibits excellent UV light stability for a SBR polymer.

### Unique Features

- ▶ Cold polymerized styrene-butadiene elastomer
- ▶ Ultraviolet light stability
- ▶ Naphthenic oil extended for improved processing

### Applications

- ▶ Coating fabrics
- ▶ White sidewalls and tires carcasses
- ▶ Footwear and mechanical rubber goods

### Typical Properties

<u>Property</u>	<u>Test Method*</u>	<u>Typical</u>
Polymer, parts .....	—	100
Oil, parts – Naphthenic .....	—	37.5
Mooney viscosity, MML 1+4 (100°C) .....	—	47 - 57
Bound Styrene, Weight % .....	—	22.5 – 24.5
Organic acid, Weight % .....	—	4.0 – 6.0
Soap, Weight % .....	—	0.5 Max.
Ash, Weight % .....	—	0.70 Max.
Volatile matter, Weight % .....	ZS 1008K	0.75 Max.
Emulsifier .....	—	Mixed acid
Coagulant .....	—	Acid
Stabilizer .....	—	Non-staining
Specific gravity, g/cc (bale).....	ASTM D-792	0.93
Physical form**, lbs/bale .....	—	80.0 (36 kg)

**SBR 1778 is finds use in applications such as coated fabrics, white sidewalls, tire carcasses, footwear and mechanical goods, especially where non-staining, non-discoloration and very light color is desired.**

\* Company Test Methods

\*\* This product is available in 80 lb rectangular bales individually wrapped in 1.5 mil, low melting point film and shipped in returnable aluminum OTD.

**Note:** Antioxidant is added to this polymer to provide protection during manufacture and storage. The end user's process may require additional antioxidant protection.

## SBR 1778 Elastomer

### Rheometric Properties (MDR 2000 rheometer)

<u>Property</u>	<u>Result</u>
M <sub>L</sub> lbf-in .....	0.8 – 2.8
dN-m .....	0.9 – 3.2
M <sub>H</sub> lbf-in .....	9.8 – 13.8
dN-m .....	11.1 – 15.6
t <sub>s</sub> 1, minutes .....	5.0 – 7.0
t' 50, minutes .....	8.1 – 12.1
t' 90, minutes .....	14.0 – 19.6

### MRG Test Recipe (ASTM 3185 2B)

	<u>Weight</u>	<u>Reference Material</u>
SBR 1778 oil-extended elastomer .....	137.5	
Zinc oxide .....	3.0	IRM 91A
Sulphur .....	1.75	NIST SRM 371
Stearic acid .....	1.0	NIST SRM 372
Oil furnace black .....	68.75	IRB #8
TBBS .....	1.38	NIST RM 8384

**SBR 1778 is a general-purpose cold polymerized, naphthenic oil-extended elastomer. It exhibits excellent UV light stability for a SBR polymer. Key applications include coated fabrics, white sidewalls, tire carcasses, footwear and mechanical goods, especially where non-staining, non-discoloration and very light color is desired.**

---

**Notice:** All information supplied by or on behalf of Lion Elastomers LLC in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Lion Elastomers LLC assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use made of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Lion Elastomers LLC for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.